

Europäische Patentamt
European Patent Office
Office européen des brevets



(11) **EP 0 719 797 A2**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
03.07.1996 Bulletin 1996/27

(51) Int Cl.⁶: **C08F 10/00, C08F 4/606,
C08F 4/602**

(21) Application number: **95500174.8**

(22) Date of filing: **20.12.1995**

(84) Designated Contracting States:
AT BE DE FR GB IT NL PT SE

• **Munoz-Escalona Lafuente, Antonio**
E-28223 Pozuelo de Alarcon (Madrid) (ES)

(30) Priority: **30.12.1994 ES 9402690**

(74) Representative: **Garcia Cabrerizo, Francisco**
OFICINA GARCIA CABRERIZO S.L.
Vitruvio 23
28006 Madrid (ES)


(72) Inventors:
• **Michiels Vega, Wilfried**
E-28804 Alcala de Henares (Madrid) (ES)

(54) **Process for obtaining polyolefins with broad bimodal or multimodal molecular weight distributions**

(57) The process is characterised by the use of catalyst systems consisting of a single metallocene catalyst activated with mixtures of at least 2 co-catalysts. The co-catalysts are aluminium alkyls, aluminoxanes or boron compounds. Different active centres are produced in the catalyst through the use of these mixed co-catalyst systems, each having different rates of initiation and completion of the polymerisation reaction, which give rise to polyolefins with different molecular weights, resulting in products with broad bimodal or multimodal molecular weight distributions and the incorporation of comonomer can be controlled by appropriate selection of

the metallocene and use of combinations of different types of co-catalysts, as well as by varying the reactor pressure, the reaction temperature and the molar ratios between the various components of the catalyst system. A broad bimodal or multimodal molecular weight distribution can be achieved in both the presence and absence of hydrogen during the polymerisation reaction. Likewise broad bimodal and multimodal molecular weight distributions can be obtained in polymers by varying the order in which the components of the catalyst system are added.

This process may also be used with both homogeneous and heterogeneous metallocene catalysts.



Description

This invention relates to a process for obtaining broad bimodal or multimodal molecular weights.

5. STATE OF THE ART

It is known that some metallocenes such as bis(cyclopentadienyl) titanium or dialkyl zirconium in combination with aluminium alkyls as co-catalyst form homogeneous systems which are useful for the polymerisation of ethylene. German patent 2,608,863 describes the system of dialkyl bis(cyclopentadienyl) titanium with trialkyl aluminium.

The controlled hydrolysis of aluminium alkyls leads to the formation of species which include Al-O bonds called aluminoxanes. Kaminsky et al. (Adv. Organomet. Chem. 18, 99, 1980) have demonstrated that aluminoxanes in combination with chlorinated metallocenes produce very active catalytic systems for the polymerisation of ethylene. The need to reduce or eliminate aluminoxanes, as these are highly flammable, and are used in large proportions in relation to the metal in polymerisation reactions, led to the use of bulky boron compounds which replaced the aluminoxane in stoichiometric molar relationships with respect to the metal of the metallocene, as described in the patents by Turner, EP 277004 and Ewen et al., EP 426637. The metallocenes used in these patents should be dialkyl derivatives, as boron compounds do not have any alkylating capacity. Alkylated metallocenes are highly unstable with water, oxygen and air, with the result that a large proportion of the metallocene present becomes deactivated before polymerisation starts, as it is used up in reacting with the impurities which are present in the medium which have not been eliminated previously. This does not happen when aluminium compounds such as aluminoxane are used, as these act to eliminate impurities from the reaction medium avoiding deactivation of the metallocene.

The use of metallocenes in combination with aluminium alkyls and aluminoxanes and boron compounds has been described by Razavi et al. in CA 2,027,144 for the polymerisation of syndiotactic polyolefins, with the objective of using small quantities of aluminium compound to remove the impurities and alkylate the metallocene. More recently, Chien et al. (Macromol. Chem. Macromol. Symp., 66, 141-156, 1993) have also used small quantities of aluminium alkyls, generally triethyl aluminium or triisobutyl aluminium, with the same object of removing impurities and alkylating the chlorinated metallocene, finally adding the boron compound as an activator for the reaction. This system makes it possible to use chlorinated metallocenes, which are stable in air, reducing the amount of aluminium compounds in the catalyst system.

On the other hand these authors comment that the use of these alkyl aluminiums together with these boron compounds is not obvious, because secondary B-H elimination reactions, or reactions with the boron compound which interfere with the catalytic system, may occur. Many patents have appeared in the last year claiming the use of these mixed co-catalyst systems, e.g. Mitsubishi Petrochemical Co. Ltd. (EP 574258, JP 5295021); Tosoh Corp. (JP 5339316, JP 5310829, JP 5301919, EP 570982, JP 5255423, JP 5239140); Idemitsu Kosan Co. Ltd. (JP 5331219, WO 9324541, JP 5320258-60, JP 5320245-48, JP 5271339, JP 5262823, JP 5262827, JP 5043618); Mitsui Toatsu (JP 5155927, JP 5140221). All these patents claim the use of a smaller quantity of aluminoxane as advantages in the use of mixed co-catalysts, and greater activity and better properties for the polymer, such as e.g. improved processability, high heat resistance, good transparency, etc.

The term "bimodal or multimodal molecular weight distribution" means that two or more peaks of different molecular weight can be seen in chromatograms obtained by gel chromatography (GPC), which represent the molecular weight as a function of the relative proportion of polymer having a specific molecular weight.

Polyolefins which have bimodal or multimodal molecular weight distributions, like polyethylene, can be transformed into articles by extrusion moulding, hot shaping, spin moulding, etc., and in general their most common applications are for tubing, films and articles made by the blowing technique. The advantages over other polyolefins which do not have multimodal molecular weight distributions are easier and faster processing with a reduced energy requirement. In addition to this, bimodal polyolefins show less flow disturbances when molten and are preferred on account of their improved properties such as a better balance between rigidity and resistance to cracking through environmental agents.

There are in the literature different ways to obtain polymers with broad bimodal or multimodal molecular weight distributions, such as the use of reactors in series, performing polymerisation with a catalyst in the absence of hydrogen (which acts as a chain transfer agent reducing the molecular weight) in the first of these reactors, yielding a high molecular weight fraction, and then passing the polymer through a second reactor in which the polymerisation is continued in the presence of hydrogen to produce another fraction of lower molecular weight. Examples of this process are the patents by Morita et al., US 4,338,424, Kuroda et al. US 4,414,369, Rafaut US 4,703,094, Kato et al., US 4,420,592. These methods to produce polymers with a multimodal molecular weight distribution are consequently expensive, complicated and require a longer time, and require more complex plant.

Another way of obtaining these multimodal polymers is through the use of a single reactor, but using mixtures of two or more different catalysts. Each catalyst produces a polymer having a different molecular weight and molecular weight distribution according to the polymerisation reaction rate constants for each catalyst, or as a result of differences

in reactive behaviour to different monomers and/or the presence of H₂, e.g. Ewen et al., EP 128045, use mixtures of different metallocenes, with different rates of propagation and reaction with respect to the same monomer. In another patent, EP 128046, Ewen et al. use mixtures of metallocenes with different reactivities to different monomers. With the same object Stricklen et al., US 4,939,217 and US 5,064,797, on the other hand use two or more metallocenes alkylated with MAO, with a different behaviour to H₂, obtaining polymers with different molecular weights. In another patent, WO 9215619, Stricklen et al. effect polymerisation in two stages, the first being a homopolymerisation in the presence of H₂ and the second a copolymerisation in the presence of H₂. Ewen et al., EP 310734, use mixtures of two chiral stereorigid metallocenes for the same purpose. However, it is difficult to control the feed of the two catalysts, and, as the particles are not of uniform size, segregation processes occur during storage and transfer of the polymer resulting in non-homogeneous polymer mixtures.

This invention claims the manufacture of polymers or copolymers of alpha-olefins with broad bimodal or multimodal molecular weight distributions in a single reactor using catalyst systems which differ from those previously patented in that a single metallocene catalyst is used in combination with mixtures of two or more compounds which act as co-catalysts. These polymers are obtained in good yield and with the good processability characteristics and properties described above.

DETAILED DESCRIPTION OF THE INVENTION


This invention is characterised by the manufacture of polyolefins having broad bimodal and multimodal molecular weight distributions using a) a single metallocene catalyst and b) at least two co-catalysts as the catalyst system. The system provided has different active centres, with different polymerisation reaction initiation and rate constants as are required for the formation of polymer fractions having different molecular weights. The difference from the other patents described, based on mixtures of catalysts, is the formation of a catalyst system from a single catalyst which is capable of forming multiple active centres.

In particular the polymers according to the invention are ethylene homopolymers, but nevertheless the use of small quantities of higher alpha-olefins having from 3 to 10 carbon atoms and preferably from 4 to 8 carbon atoms can produce ethylene copolymers. Illustrated examples of these higher alpha-olefins are 1-butene, 1-hexene and 1-octene.


In this invention, ethylene, alone or with smaller quantities of alpha-olefin, is polymerised in the presence of a catalyst system which consists of a) a single metallocene as catalyst and b) at least two compounds as co-catalysts.

The metallocenes used are organometallic coordination compounds of mono, di and tricyclopentadienyl and its transition metal derivatives from groups 4b, 5b and 6b of the Periodic Table of Elements.

The preferred metallocenes for use in accordance with this invention are represented by the general formulae:



or



where (C₅R'_m) is cyclopentadienyl or substituted cyclopentadienyl, each R' may be the same or different, and may be hydrogen, monohydrocarbon radicals such as alkyl, alkenyl, aryl, alkylaryl or arylalkyl containing 1 to 20 carbon atoms, or two adjacent carbon atoms joined to form a C4-C6 ring, or various condensed rings, R'' is an alkylene radical containing between 1 and 4 carbon atoms, a dialkyl germanium or silicon radical, or an alkylphosphine or amine radical joining two (C₅R'_m) rings, Q is a hydrocarbon radical such as aryl, alkyl, alkenyl, alkyl aryl, aryl alkyl containing from 1 to 20 carbon atoms, or halogen, and each one may be the same or different, Q' is an alkylidene radical containing from 1 to 20 carbon atoms, Me is a transition metal from groups 4b, 5b or 6b of the Periodic Table of elements, s is 0 or 1, p is 0.1 or 2; when p is 0, s is 0; m is 4 if s is 1 and m is 5 if s is 0.

Examples of hydrocarbon radicals are methyl, ethyl, propyl, butyl, amyl, isoamyl, hexyl, isobutyl, heptyl, octyl, nonyl, decyl, cetyl, 2-ethylhexyl, phenyl and the like.

Examples of alkylene bridges are methylene, ethylene, propylene and the like.

Examples of halogen atoms are chlorine, bromine and iodine, the preferred halogen being chlorine.

Examples of alkylidene radicals are methylidene, ethylidene and propylidene.

The metallocenes used in accordance with this invention are preferably mono, bis or tris cyclopentadienyl or substituted cyclopentadienyls of titanium (IV) or zirconium (IV) represented in the general formula.

Illustrative but not restrictive examples of the metallocenes used in this invention are titanium monocyclopentadienyls such as cyclopentadienyl titanium trichloride, pentamethylcyclopentadienyl titanium trichloride, titanium biscyclopentadienyls such as bis(cyclopentadienyl) titanium dichloride, dimethyl bis(cyclopentadienyl) titanium, diphenyl bis(cyclopentadienyl) titanium, bis(indenyl) titanium dichloride, dimethyl bis(indenyl) titanium, diphenyl bis(cyclopentadienyl) titanium, diphenyl or dihalo bis(methylcyclopentadienyl) titanium, dialkyl, trialkyl, tetraalkyl and pentaalkyl cyclopentadienyl derivatives such as diphenyl or dihalo, bis(1, 2-dimethyl cyclopentadienyl) titanium, dimethyl or dihalo bis

(1,2-diethyl cyclopentadienyl) titanium and other complex dialkyls or dihalides.

Illustrative but not restrictive examples of appropriate zirconium metallocenes for use in this invention are zirconium monocyclopentadienyls such as cyclopentadienyl zirconium dichloride, pentamethylcyclopentadienyl zirconium trichloride, zirconium biscyclopentadienyls such as bis(cyclopentadienyl) zirconium dichloride, dimethyl bis(cyclopentadienyl) zirconium, diphenyl bis(cyclopentadienyl) zirconium, substituted cyclopentadienyl alkyls such as dimethyl or dihalo bis(ethylcyclopentadienyl) zirconium, diphenyl or dihalo bis(methylcyclopentadienyl) zirconium, dialkyl, trialkyl, tetraalkyl and pentaalkyl cyclopentadienyl (pentamethylcyclopentadienyl) (cyclopentadienyl) zirconium dichloride, dimethyl or dihalo bis (pentamethylcyclopentadienyl) zirconium, dimethyl bis (1,2-dimethylcyclopentadienyl) zirconium, and others of the kind.

Silicon, phosphorus and carbon bridges between cyclopentadienyl rings such as e.g. dimethyl or dihalo dimethylsilylbis (cyclopentadienyl) zirconium, dimethyl or dihalo methylphosphene bis(cyclopentadienyl) zirconium, dimethyl or dihalo methylene bis(cyclopentadienyl) zirconium, carbenes represented by the formula $CP_2Zr = CH_2P(C_6H_5)_2CH_3$, and derivatives of these compounds such as $CP_2ZrCH_2CH(CH_3)CH_2$.

Biscyclopentadienyl hafnium dichloride, dimethyl bis(cyclopentadienyl) hafnium, bis(cyclopentadienyl) vanadium dichloride are illustrative of other metallocenes.

The compounds which can act as co-catalysts in the polymerisation of olefins and which are useful for use in accordance with this invention are well known in the literature, and can be divided into three groups:


(a) Aluminium compounds of general formula:




where the R'' groups, which are the same or different, may be alkyls or aryls containing from 1 to 20 carbon atoms, or halogens, and Al is aluminium.

Illustrative but not restrictive examples of compounds in this group of aluminium compounds are trimethyl aluminium, triethyl aluminium, triisobutyl aluminium, aluminium diethyl chloride, aluminium monoethyl chloride, triphenyl aluminium and the like.

(b) Aluminium compounds incorporating Al-O bonds (aluminoxanes) of general formula:



or




where R is an alkyl or aryl group containing from 1 to 20 carbon atoms, and n is a number from 1 to 20. These compounds are known in the literature as aluminoxanes and have two different structures, linear and cyclic. In this invention the compound when R = methyl is preferred, i.e. methyl aluminoxane (MAO).

(c) Boron compounds having the general formulae:



OR



where B is boron, X_1, X_2, X_3, X_4 , which are the same or different, may be hydride, halide, alkyl containing from 1 to 20 carbon atoms, substituted alkyls containing from 1 to 20 carbon atoms, in which one or more hydrogens are substituted by halogens, metallohydrocarbon radicals (organometalloids) in which each substitution contains from 1 to 20 carbon atoms and the metal is selected from group 4a of the Periodic Table of elements, aryl, substituted aryls containing from 6 to 20 carbon atoms. Nonrestrictive examples of these substituents are phenyl, naphthyl and anthracenyl. The aryl groups can be substituted by other groups such as alkoxy and alkylamido radicals, fluorine or halogen-substituted hydrocarbon groups.

And it may be a Bronsted acid, such as H^+ , ammonium or substituted ammonia cations in which up to 3 of the hydrogen atoms may be replaced by hydrocarbon radicals containing from 1 to 20 carbon atoms or substituted hydrocarbon radicals in which one or more of the hydrogen atoms are substituted by halogens, phosphonium radicals or substituted phosphonium radicals in which up to 3 hydrogens may be substituted by hydrocarbon radicals containing from 1 to 20 carbon atoms, or substituted hydrocarbon radicals in which one or more of the hydrogens may be substi-

tuted by halogens, or carbene radicals in which up to 3 of the hydrogens may be replaced by hydrocarbon radicals containing from 1 to 20 carbon atoms, or substituted hydrocarbon radicals in which one or more hydrogens may be substituted by halogens.

Illustrative but not restrictive examples in accordance with their use in this invention are triphenyl borane, pentafluorophenyl diphenyl borane, tris(pentafluorophenyl) borane, tris(3,5-di-trifluoromethylphenyl) borane, triethyl ammonium tetraphenyl borate, tripropyl ammonium tetraphenyl borate, tris(n-butyl) ammonium tetraphenyl borate, trimethyl ammonium tetrakis(p-tolyl) borate, tributyl ammonium tetrakis(pentafluorophenyl) borate, tributylammonium tetrakis(3,5-dimethylphenyl) borate, and the like. Other examples of N,N'-dialkylanilino salts are for example N,N'-diethylanilino tetraphenyl borate, N,N'-dimethylanilino tetrakis(pentafluorophenyl) borate, triarylphosphonium derivative salts such as e.g. triphenylphosphonium tetraphenylborate, tri(methylphenyl)phosphonium tetrakis(pentafluorophenyl) borate, carbene derivatives such as e.g. triphenylcarbene tetrakis(pentafluorophenyl) borane and similar compounds.

In accordance with this invention these compounds, which act as co-catalysts in the catalytic system together with the metallocene, should take part forming mixtures of at least two compounds for the polymerisation of olefins producing polymers having broad bimodal and multimodal molecular weight distributions.

Combinations between the three groups of compounds formulated above may be used in this invention, and the following combinations are appropriate:

- Aluminium alkyls and aluminoxanes,
- Aluminium alkyls and boron compounds,
- Aluminium alkyls and aluminoxanes and boron compounds,
- Aluminoxanes and boron compounds.

The proportions used in these co-catalyst systems containing more than one co-catalyst vary depending on the metallocene compound used. The molar ratios between the aluminium compounds (aluminium alkyls and/or aluminoxanes) and transition metals of the metallocene vary from 1:1 to 10^8 :1, preferably from 5:1 to 10^5 :1. Molar ratios between aluminium compounds (aluminium alkyls and/or aluminoxanes) and boron compounds vary from 0.01:1 to 10^4 :1, preferably from 0.1:1 to 10^3 :1. The molar ratios used between compounds of boron and the transition metal of the metallocene will be determined by the ratios between the compounds of aluminium and the transition metal and the molar ratios between the aluminium compound and the boron compound.

The distribution of molecular weights and the incorporation of co-monomer in each fraction of molecular weight is controlled by appropriate selection of the metallocene and combinations to form the mixture of co-catalysts, and the variables H_2 content, pressure and temperature, and the molar ratios between the different components of the catalyst system.

Broad bimodal or multimodal molecular weight distributions may be obtained by adding the components of the catalyst system, catalyst and co-catalysts, to the reaction medium separately or premixed. Broad bimodal or multimodal distributions can be achieved with addition in any order.

The solvents used in preparation of the catalytic system are inert hydrocarbons, particularly those inert to the catalyst system, which is sensitive to impurities such as traces of water, oxygen, air, etc. These solvents are e.g. butane, isobutane, pentane, hexane, heptane, octane, cyclohexane, methyl cyclohexane, toluene, xylene, petroleum fractions from fractions of different boiling point and the like. The co-catalyst described should be used with hydrocarbon solvents such as e.g. toluene or xylene and the like in concentrations from 0.1 M to 3.0 M, although higher or lower concentrations may be used.

The catalyst systems described in this invention are useful for the polymerisation of alpha-olefins in solution, slurries or the gas phase over a wide range of temperatures and pressures. For example temperatures may vary from -60°C to 280°C , and preferably from 40°C to 160°C . Pressures vary from 1 to 500 atmospheres or higher. The polymerisation time may vary from 1 minute to 6 hours, but frequently from 10 minutes to 2 hours.

Polymerisation in solution makes it possible to use the catalyst system as a homogeneous system, but nevertheless the catalyst system may be converted into a heterogeneous system by supporting the metallocene on typical supports, using techniques known in the literature. The supports may be inorganic supports such as silica, silica-alumina, alumina, metal oxides in general, MgCl_2 , etc., or may be organic such as polyethylene, polybutadiene, etc. The solid system is more appropriate for slurry or gas phase polymerisation.

Heterogeneous catalysts are preferable for the production of polymers such as polyethylene, as the active centres are sufficiently fixed and separated on the support, avoiding deactivation reactions between them, and generally higher molecular weights are obtained. In addition to this the particle shape, size and size distribution of the resulting polymer is better controlled using supported catalysts.

Polymers obtained according to this invention have average molecular weights which may vary from 500 to 10^7 by weight. It is also possible to use H_2 to control the molecular weight of the polymers formed, but this is not always necessary as it can also be adjusted by varying the molar ratios between the different components of the catalyst

system, the metallocene concentrations, the reaction temperature, etc.

In the examples which follow molecular weights have been determined using a Walters ALC/GPC Model 150C apparatus equipped with a Viscatek 110 viscometer using Polymer Laboratory Columns (2 x mixed bed, 10^7 and another of 10^6). Measurements were performed by dissolving the polymer samples in trichlorobenzene (TCB) at 145°C and filtering them. Irganox 1010 was used as antioxidant. The flow rate was 1 ml/min with concentrations of 1.5 mg/ml.

EXAMPLES

EXAMPLE 1a

This example serves to describe the preparation of a polymer having a narrow monomodal distribution when a metallocene and a single co-catalyst of the aluminoxane type is used. A glass reactor of 1 l capacity equipped with a mechanical stirrer, an outer jacket for temperature control, an inlet feed for monomers and gases, an inlet feed with a septum for adding doses of the catalyst system with a syringe, was dried and deoxygenated using a flow of nitrogen. 400 ml of dry n-heptane were added directly with continuous stirring (1200 rpm). The nitrogen atmosphere was removed by charging and discharging the vessel with ethylene until the solution became saturated with ethylene. This was then heated to 90°C and 2.0 mols of methyl aluminoxane (MAO, 1.5 M solution in toluene) were added. After the ethylene pressure increased to 4 bars, 5.84 mg (0.02 mmol) of bis(cyclopentadienyl) zirconium dichloride dissolved in toluene were added using a syringe. After 15 minutes the reactor was depressurised and the reaction mixture cooled. The polymer was discharged and washed with slightly acidified methanol to deactivate catalyst residues and dried to constant weight in a vacuum stove. 27.89 g of white polyethylene powder were obtained with an average molecular weight of 69000 and a polydispersity index of $M_w/M_n = 3.5$. The molecular weight distribution was narrow and monomodal.

EXAMPLE 1b

This example serves to describe the preparation of a polymer having a narrow monomodal distribution when an alkylated metallocene and a single co-catalyst of the boron compound type is used. From a flask of 500 ml capacity equipped with septum inlets and a magnetic stirrer oxygen was removed by displacement with flows of nitrogen and 200 ml of dry N-heptane were injected. This was then placed in a thermostatic bath and the nitrogen atmosphere was replaced by ethylene by successive charging and discharging with ethylene. 51.2 mg (0.1 mmoles) of tris(pentafluorophenyl) borane dissolved in toluene (0.1 M) were introduced into the flask through the septum using a syringe with a hypodermic needle. When the solution was saturated with ethylene and the temperature was 40°C , 25.0 mg (0.1 mmoles) of dimethyl bis(cyclopentadienyl) zirconium dissolved in toluene (0.1 M) were injected directly into the flask. After 15 minutes reaction 6.92 g of polyethylene having a molecular weight of $M_w = 189,000$ and a polydispersity index of $M_w/M_n = 2.4$ were obtained. The molecular weight distribution was narrow and monomodal. Both the CP_2ZrMe_2 and the $\text{B}(\text{C}_6\text{F}_5)_3$ were prepared in accordance with the methods described in the literature.

The ten examples which follow describe the production of a bimodal homopolymer or copolymer according to the method described in this invention.

EXAMPLE 2

This example describes the preparation of a bimodal polyethylene. 200 ml of dry n-heptane were injected under a nitrogen atmosphere into a dry 500 ml capacity flask from which oxygen had been removed using a flow of nitrogen, equipped with inlets provided with a septum and a magnetic stirrer. This was then placed in a thermostatic bath and the nitrogen atmosphere was replaced with ethylene by successive charging and discharging with ethylene. 10.0 mmoles of methylaluminoxane and subsequently 51.2 mg (0.1 mmoles) of tris(pentafluorophenyl) borane dissolved in toluene (0.1 M) were introduced using a syringe with a hypodermic needle. When the solution was saturated with ethylene and the temperature was 40°C , 29.2 mg (0.1 mmoles) of bis(cyclopentadienyl)zirconium dichloride dissolved in toluene (0.1 M) were injected directly into the flask. After 15 minutes reaction a polymer was obtained which was shown to be clearly bimodal when analysed by GPC. The molecular weight $M_w = 108,900$ and the polydispersity $M_w/M_n = 11.54$.

EXAMPLE 3

This example describes the preparation of a bimodal polyethylene. The method for preparing the polyethylene is similar to the procedure described in Example 2, but the boron compound was injected first, followed by the metallocene and finally the aluminoxane. The resulting polyethylene had a $M_w = 86,600$ and a polydispersity of $M_w/M_n = 12.51$, the molecular weight distribution of the polymer being clearly bimodal, as shown by its chromatogram.

EXAMPLE 4

This example describes the preparation of a bimodal polyethylene. This was prepared using the procedure described in Example 2, but first injecting a prepared mixture of methylaluminoxane and bis(cyclopentadienyl) zirconium dichloride in a molar ratio 10:1 which had been aged for 24 hours and in quantities such that the concentrations in the flask were 6.0 mmoles of MAO and 0.06 mmoles of CP_2ZrCl_2 . 0.1 mmoles of $\text{B}(\text{C}_6\text{F}_5)_3$ were then added. The polyethylene had a molecular weight of $M_w = 115,500$ and a polydispersity of $M_w/M_n = 10.35$. The resulting chromatogram was clearly bimodal.

EXAMPLE 5

This example describes the preparation of a bimodal polyethylene. The preparation was in accordance with the procedure described in Example 1a, but 10.0 mmoles of methylaluminoxane and 0.05 mmoles of $\text{B}(\text{C}_6\text{F}_5)_3$ were injected prior to injecting 14.62 mg (0.06 mmoles) of bis(cyclopentadienyl) zirconium dichloride. The chromatogram of the resulting polymer showed a bimodal molecular weight distribution as shown in the chromatogram in Figure 1.

EXAMPLE 6

This example describes the preparation of a bimodal ethylene-hexene copolymer. The copolymer in this example was prepared in accordance with the procedure described in Example 1a, adding 1.97 ml (15.87 mmoles) of 1-hexene when the reactor was saturated with ethylene and at 40°C. Once this had been added the temperature was raised to 90°C. 2.0 mmoles of MAO, 0.02 mmoles of $\text{B}(\text{C}_6\text{F}_5)_3$ and 0.02 mmoles of zirconocene were then added. After 15 minutes reaction 27.07 g of a polyethylene having a molecular weight of $M_w = 62,400$ and a polydispersity of $M_w/M_n = 8.2$, with a clearly bimodal chromatogram, were obtained.

EXAMPLE 7

This example describes the preparation of a bimodal polyethylene. The polyethylene in this example was prepared in accordance with the procedure described in Example 1a, but adding 2.0 mmoles of MAO and 0.02 mmoles of $\text{B}(\text{C}_6\text{F}_5)_3$. The reaction was completed in the presence of 0.2 bar of hydrogen. After 15 minutes reaction 28.31 g of a polyethylene whose molecular weight distribution from the chromatogram was clearly bimodal, as shown by the chromatogram in Figure 2, was obtained.

EXAMPLE 8

This example describes the preparation of a bimodal polyethylene. It was prepared in accordance with the procedure described in Example 2, but using 50.0 mmoles of methylaluminoxane, 0.1 mmoles of $\text{B}(\text{C}_6\text{F}_5)_3$ and 36.23 mg (0.1 mmoles) of (pentamethylcyclopentadienyl) (cyclopentadienyl) zirconium dichloride. The resulting polymer yielded a bimodal chromatogram, had a molecular weight of $M_w = 105,900$ and a polydispersity of $M_w/M_n = 8.57$. The zirconocene was synthesised in accordance with the methods described in the literature.

EXAMPLE 9

This example describes the preparation of a bimodal polyethylene. It was prepared in accordance with the procedure described in Example 2, but using 10.0 mmoles of methylaluminoxane, 5.0 mmoles of trimethyl aluminium and 0.1 mmoles of bis(cyclopentadienyl) zirconium dichloride. The polyethylene had a molecular weight of $M_w = 50,800$ and a polydispersity of $M_w/M_n = 6.06$. The molecular weight distribution was clearly bimodal as shown by its chromatogram.

EXAMPLE 10

This example describes the preparation of a bimodal polyethylene. It was prepared in accordance with the procedure described in Example 2, but using 15.0 mmoles of triethylaluminium, 0.1 mmoles of $(\text{C}_6\text{F}_5)_3$ and 29.02 mg (0.1 mmoles) of bis(cyclopentadienyl) zirconium dichloride. The bimodal polymer had a molecular weight of $M_w = 103,600$ and a polydispersity of $M_w/M_n = 6.79$. The GPC chromatogram indicated its bimodal nature.

EXAMPLE 11

This example describes the preparation of a bimodal polyethylene. It was prepared in accordance with the proce-

Example 2, but using 10.0 mmoles of methylaluminoxane, 15.0 mmoles of triisobutyl aluminium and 0.1 mmoles of biscyclopentadienyl zirconium dichloride. The molecular weight distribution was found to be clearly bimodal by chromatography, as shown by the chromatogram in Figure 3.


EXAMPLE 12

This example describes the preparation of a bimodal polyethylene. It was prepared in accordance with the procedure described in Example 2, but using 15.0 mmoles of methyl aluminoxane, 7.5 mmoles of triisobutylaluminoxane, 0.1 mmoles of $B(C_6F_5)_3$ and 29.02 mg (0.1 mmoles) of biscyclopentadienyl zirconium dichloride. The polymer had a molecular weight of $M_w = 97,500$ and a polydispersity of $M_w/M_n = 6.89$. The molecular weight distribution as shown by the GPC chromatogram was clearly bimodal.


Claims

1. A process for obtaining homopolymers of alpha-olefins containing from 2 to 20 carbon atoms and copolymers of different alpha-olefins containing from 2 to 20 carbon atoms with wide bimodal or multimodal molecular weight distributions, characterised by use of catalytic systems consisting of two subsystems a) and b):

(a) a single supported or unsupported metallocene catalyst, being mono, di and tricyclopentadienyl and their derivatives of transition metals in groups 4b, 5b, 6b of the Periodic Table of elements, represented by the general formulae:



or



where $(C_5R'_m)$ is cyclopentadienyl or substituted cyclopentadienyl, each R' may be the same or different, and may be hydrogen, monohydrocarbon radicals such as alkyl, alkenyl, aryl, alkylaryl or arylalkyl containing from 1 to 20 carbon atoms, or two adjacent carbon atoms joined to form a C4-C6 ring, or various condensed rings, R'' is an alkylene radical containing from 1 to 4 carbon atoms, a dialkyl germanium or silicon radical, or an alkylphosphine or amino radical joining two $(C_5R'_m)$ rings, Q is a hydrocarbon radical such as aryl, alkyl, alkenyl, alkylaryl, arylalkyl containing from 1 to 20 carbon atoms, or halogen, and each one may be the same or different, Q' is an alkylidene radical containing from 1 to 20 carbon atoms, Me is a transition metal in groups 4b, 5b or 6b of the Periodic Table of elements, s is 0 or 1, p is 0, 1 or 2; when p is 0, s is 0; m is 4 if s is 1 and m is 5 if s is 0. (b) a mixture of two or more co-catalysts selected from the following groups i), ii) and iii):

- 1) Aluminium compounds having the general formula:




where the R'' groups, which may be the same or different, may be alkyls or aryls containing from 1 to 20 carbon atoms, or halogens, and Al is aluminium,

- ii) Aluminium compounds having Al-O bonds (aluminoxanes) corresponding to the general formulae:




or




where R is an alkyl or aryl group containing from 1 to 20 carbon atoms, and n is a number from 1 to 20,

- iii) Boron compounds corresponding to the general formulae:






OR




where B is boron, X^1 , X^2 , X^3 , X^4 , which are the same or different, may be hydride, halide, alkyl containing from 1 to 20 carbon atoms, substituted alkyls containing from 1 to 20 carbon atoms, in which one or more hydrogens are substituted by halogens, metal hydrocarbon radicals (organometalloids) in which each substitution contains from 1 to 20 carbon atoms and the metal is selected from group 4a of the Periodic Table of elements, aryl, substituted aryls containing from 6 to 20 carbon atoms. The aryl groups can be substituted by other groups such as alkoxy and alkylamido or fluoro radicals or halogen-substituted hydrocarbon groups,

and may be a Bronsted acid, such as H^+ , ammonium or substituted ammonium cations in which up to 3 of the hydrogen atoms may be replaced by hydrocarbon radicals containing from 1 to 20 carbon atoms or by substituted hydrocarbon radicals in which one or more of the hydrogen atoms are substituted by halogens, phosphonium radicals or substituted phosphonium radicals in which up to 3 hydrogens can be substituted by hydrocarbon radicals containing from 1 to 20 carbon atoms, or by substituted hydrocarbon radicals in which one or more of the hydrogens may be substituted by halogens, or carbene radicals in which up to 3 of the hydrogens may be substituted by hydrocarbon radicals containing from 1 to 20 carbon atoms, or substituted hydrocarbon radicals in which one or more of the hydrogens may be substituted by halogens.

2. A process for the preparation of homopolymers in accordance with claim 1, characterised in that the olefin is ethylene.
3. A process for preparing copolymers in accordance with claim 2, characterised in that the co-monomer is 1-butene, 1-hexene or 1-octene and is incorporated at random.
4. A process for the preparation of homopolymers and copolymers in accordance with claim 1, characterised by the use of hydrocarbon solvents under inert conditions for the catalyst system and reaction temperatures between -60°C and 280°C , preferably between 40°C and 160°C , reactor pressures between 1 and 500 atmospheres, in the presence or absence of H_2 as a regulator of the molecular weight of the polymer.
5. A process according to claim 1, characterised in that the metallocene is supported or unsupported bis(cyclopentadienyl) zirconium dichloride, in which the aluminium compound is an aluminium alkyl, preferably trimethyl aluminium, triethyl aluminium or triisobutyl aluminium, in which the aluminoxane is methyl aluminoxane, and in which the boron compound is tris(pentafluorophenyl) borane.
6. A process according to claim 1, characterised in that the catalyst composition has molar ratios of aluminium compound to metallocene catalyst metal from 1.0:1.0 to 10^8 :1.0, preferably from 5.0:1.0 to 10^5 :1.0 and molar ratios of aluminium compound and/or aluminoxane to boron from 0.01:1 to 10^4 :1, preferably from 0.1:1 to 10^3 :1.0.
7. The product prepared according to claims 1, 2, 3, 4, 5 and 6.





Eur päisch s Patentamt
European Patent Office
Office européen des brevets



(11) EP 0 719 797 A3

(12) EUROPEAN PATENT APPLICATION

(88) Date of publication A3:
23.04.1997 Bulletin 1997/17

(51) Int Cl.⁶: C08F 10/00, C08F 4/606,
C08F 4/602

(43) Date of publication A2:
03.07.1996 Bulletin 1996/27

(21) Application number: 95500174.8

(22) Date of filing: 20.12.1995

(84) Designated Contracting States:
AT BE DE FR GB IT NL PT SE

• Munoz-Escalona Lafuente, Antonio
E-28223 Pozuelo de Alarcon (Madrid) (ES)

(30) Priority: 30.12.1994 ES 9402690

(74) Representative: Garcia Cabrerizo, Francisco
OFICINA GARCIA CABRERIZO S.L.
Vitrivio 23
28006 Madrid (ES)

(71) Applicant: REPSOL QUIMICA S.A.
E-28046 Madrid (ES)

(72) Inventors:
• Michiels Vega, Wilfried
E-28804 Alcala de Henares (Madrid) (ES)

(54) Process for obtaining polyolefins with broad bimodal or multimodal molecular weight distributions

(57) The process is characterised by the use of catalyst systems consisting of a single metallocene catalyst activated with mixtures of at least 2 co-catalysts. The co-catalysts are aluminium alkyls, aluminoxanes or boron compounds. Different active centres are produced in the catalyst through the use of these mixed co-catalyst systems, each having different rates of initiation and completion of the polymerisation reaction, which give rise to polyolefins with different molecular weights, resulting in products with broad bimodal or multimodal molecular weight distributions and the incorporation of comonomer can be controlled by appropriate selection of

the metallocene and use of combinations of different types of co-catalysts, as well as by varying the reactor pressure, the reaction temperature and the molar ratios between the various components of the catalyst system. A broad bimodal or multimodal molecular weight distribution can be achieved in both the presence and absence of hydrogen during the polymerisation reaction. Likewise broad bimodal and multimodal molecular weight distributions can be obtained in polymers by varying the order in which the components of the catalyst system are added.

This process may also be used with both homogeneous and heterogeneous metallocene catalysts.




FIG. 1

EP 0 719 797 A3



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 95 50 0174

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
X	EP 0 284 707 A (COSDEN TECHNOLOGY) * example 1 * * claims 1,16-18 * * figures B-D * * page 7, line 13 - line 26 * * page 5, line 2 - line 11 * ---	1,4,6,7	C08F10/00 C08F4/606 C08F4/602
P,X	WO 95 30698 A (DSM) * page 26; example IX * * page 28; example IX; table 4 * ---	1,2,4,6,7	
X	EP 0 513 808 A (PHILLIPS) * page 3, line 24 - line 31 * * page 5; example I * * table I, run 2,7,8 * * page 6, line 58 - page 7, line 2 * * table II, run 18 * * page 8, line 55 * * page 5, line 30 - line 35 * ---	1,2,4-7	
X	EP 0 573 120 A (SOLVAY) * page 10, line 38 - line 45 * * examples 1,2,6,7 * * claims 19,31 * ---	1,2,4,6,7	TECHNICAL FIELDS SEARCHED (Int.Cl.6) C08F
A	EP 0 594 218 A (MITSUI) * page 16; example 10 * * example 11; table 3 * ---	1-7	
A	EP 0 612 768 A (TOSOH) * claim 1 * * page 4 - page 5; example 1 * * comparative example 3 * * page 8; example 5; table 2 * ---	1-7	
		-/--	
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 25 February 1997	Examiner Fischer, B
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1500 01.92 (POM/COJ)



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 95 50 0174

DOCUMENTS CONSIDERED TO BE RELEVANT		
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim
A	DIE MAKROMOLEKULARE CHEMIE, RAPID COMMUNICATIONS, vol. 14, no. 12, December 1993, pages 765-770, XP000411902 * page 768, paragraph 2; figures A,B * -----	1
		CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
		TECHNICAL FIELDS SEARCHED (Int.Cl.6)
The present search report has been drawn up for all claims		
Place of search	Date of completion of the search	Examiner
THE HAGUE	25 February 1997	Fischer, B
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons</p> <p>***** & : member of the same patent family, corresponding document</p>		

EPO FORM 1502 (01.92) (P4/CN)